

GRACE TOP-CAST™ Top-Surface Retarder

Product Description

Grace Top-Cast™ is a water-based, top-surface retarder which does not require covering with plastic for protection. It is available in 11 depths of etch, each one color and number coded for safety and convenience.

Uses

Ideal for poured-in-place flatwork and the top surface of precast panels. The wide selection of grades available provides a comprehensive range of effects, from a simulated light acid wash or sand blast finish up to full exposure of 1¼ in. (32 mm) aggregate.

Performance

Each product grade creates a unique degree of reaction to produce the desired effect on the surface mortar. The retarding chemicals diffuse into the paste during the first hours of curing, and slow down the cement hydration reaction. During the next 16+ hours of curing the bulk concrete hardens, except where the cement matrix has been retarded.

Product Advantages

- Comprehensive range of etch depths
- Excellent depth of etch control
- Color coded products
- Heavily pigmented for ease of application
- Excellent coverage rates
- Solvent free, odorless
- Heat resistance up to 150°F

The retarded surface can then be removed by water or pressurized water, revealing the aggregate in the concrete mix.

Application Information

Always prepare small test panels to determine the most suitable grade to obtain the desired depth of etch. When pouring test samples, always simulate job site conditions as well as mix designs to be used on the project to establish the proper grade selection and procedures.

Application:

In preparation for pouring of concrete, protect all curbs, borders, adjacent stones, pavers, etc. with a coat of Pieri® Face Off. Allow coating to dry before pouring concrete. Pour concrete and float or trowel finish.



Shake well before application. Apply Grace Top-Cast uniformly to the wet concrete after the initial bleed water rises to the surface. Spray with a low-pressure sprayer (plastic preferred) until the surface has a complete hiding coat. Do not apply too sparingly. Use water for clean up. Once dry (i.e. 1–2 hours after application), Grace Top-Cast provides excellent protection against intermittent rain.

Removal:

The retarded cement matrix is normally washed away the next day, using high-pressure water.

When using certain mix designs, especially in warmer temperatures, it may be necessary to remove the retarded matrix the same day for best results, particularly when using the lightest etches.

Coverage Rates:

Grace Top-Cast will cover approximately 175–300 ft²/gal (4.3–7.4 m²/L).

Packaging & Handling

Grace Top-Cast is available 5 gal (19 L) and 55 gal (208 L) plastic containers.

Storage

Grace Top-Cast has a shelf life of one year from date of manufacture, in closed original container.

All precautions defined on the MSDS (Material Safety Data Sheet) for Grace Top-Cast must be followed.

Grace Top-Cast Grade Guide

(Based on 6 Sack Mix*)

Stone Size	Grade
Acid Etch	03 Light Violet
Sand Blast	05 Powder Blue Violet
Up to ¼ in. Up to 6.5 mm	15 Yellow
⅛ to ¼ in. 3.0 to 6.5 mm	25 Beige
⅛ to ⅜ in. 3.0 to 9.5 mm	50 Canary Green
⅛ to ⅜ in. 3.0 to 9.5 mm	75 Blue
⅜ to ½ in. 9.5 to 13 mm	100 Gray
⅜ to ⅝ in. 13 to 16 mm	125 Pink
⅜ to ⅝ in. 13 to 16 mm	150 Green
⅝ to 1 in. 16 to 25 mm	200 Salmon
1 to 1½ in. 25 to 38 mm	250 Orange

*564 lbs/yd³ or 355 kg/m³ of cement

www.gracedecorativeconcrete.com

www.graceconstruction.com

North American Customer Service: 1-877-4AD-MIX1 (1-877-423-6491)

Pieri is a registered trademark and Top-Cast is a trademark of W. R. Grace & Co.–Conn.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the users' consideration, investigation and verification, but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use which would infringe any patent or copyright. W. R. Grace & Co.–Conn., 62 Whittemore Avenue, Cambridge, MA 02140. In Canada, Grace Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This product may be covered by patents or patents pending.
DEC-001C Printed in U.S.A. 11/07

Copyright 2007. W. R. Grace & Co.–Conn.
FA/LI/3M

